U.S. RUBBER CORP.

CHEMICAL RESISTANCE MATRIX

BELT TYPE LOADSTAR	VEGETABLE OIL	ANIMAL OIL	MINERAL OIL	ACID	HYDRO CARBONS	FLAME	SUN AND OZONE
LOADSTAR GRADE 1 * 1	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Not Recommended	Some Conditions
LOADSTAR GRADE II * 2	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Not Recommended	Some Conditions
LOADSTAR SAR RUBSTONE SUPER ABRASION RESISTANT	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Not Recommended	Some Conditions
LOADSTAR SOR SUPER OIL RESISTANT	Recommended	Recommended	Recommended	Recommended	Recommended	Not Recommended	Some Conditions
LOADSTAR MOR MODERATE OIL RESISTANT	Some Conditions	Some Conditions	Recommended	Recommended	Recommended	Not Recommended	Some Conditions
LOADSTAR HOS HEAT AND OIL SERVICE	Some C onditions	Some Conditions	Recommended	Recommended	Some Conditions	Not Recommended	Recommended
HEAT GUARD 400 HEAT RESISTANT	Some Conditions	Some Conditions	Some Conditions	Recommended	Some Conditions	Not Recommended	Recommended
FLAME GUARD UNDERGROUND FLAME RETARDANT	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Recommended	Some Conditions
LOADSTAR FR ABOVE-GROUND FLAME RETARDANT	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Recommended	Some Conditions
LOADSTAR SCORF GRAIN SERVICE PREFERRED	Recommended	Some Conditions	Recommended	Recommended	Recommended	Recommended	Some Conditions
LOADSTAR FRSAR ABOVE GROUND FLAME RESISTANT SUPER ABRASION	Not Recommended	Not Recommended	Some Conditions	Recommended	Some Conditions	Recommended	Some Conditions

= Recommended = Recommended under some conditions = Not Recommended

Information presented hereon has been compiled from sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief, but is nor guaranteed to be so. Since conditions of use are beyond our control, we make no warranties, expressed or implied.

U.S. RUBBER CORP.

RECOMMENDED SERVICE TEMPERATURES

BELT TYPE	LOW TEMP LIMIT	STANDARD OPERATING TEMPERATURES	MAXIMUM HOT SERVICE TEMPERATURES
LOADSTAR GRADE 1 * 1	-30		200
LOADSTAR GRADE II * 2	-25		180
LOADSTAR SAR RUBSTONE SUPER ABRASION RESISTANT	-30		200
LOADSTAR SOR SUPER OIL RESISTANT	-30		200
LOADSTAR MOR MODERATE OIL RESISTANT	-30		200
LOADSTAR HOS HEAT AND OIL SERVICE	-20		250 Degree Fines 350 Degree Course 2" or Over 350
HEAT GUARD 400 HEAT RESISTANT	-40		250 Degree Fines 350 Degree Course 2" or Over 400
FLAME GUARD UNDERGROUND FLAME RETARDANT	-30		200
LOADSTAR FR ABOVEGROUND FLAME RETARDANT	-30		200
LOADSTAR SCORF GRAIN SERVICE PREFERRED	-30		200
LOADSTAR FRSAR ABOVE GROUND FLAME RESISTANT SUPER ABRASION	-30		200

IMPORTANT: Information presented hereon has been compiled from sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief, but is nor guaranteed to be so. Since conditions of use are beyond our control, we make no warranties, expressed or implied.

U.S. RUBBER CORPORATION - 211 NORTH LOOP 336 EAST - CONROE TX 77301 SALES 800-872-3587